



# PS 1060

## Type:

PS 1060 is a low K-value PVC homopolymer resin extender obtained by suspension polymerisation for use as an addition resin in the preparation of plastisols.

## Main uses:

- \* Coatings: floor and wallpapers, coated fabrics (artificial leather, conveyor belts, tarpaulins...),
- \* Automotive industry: car underbody sealant,
- \* Crown seals.

**LACOVYL® PS 1060 is an extender resin for Paste PVC:  
It allows to reduce plastisol viscosity and to increase mattness of the coating.**

## General characteristics:

PS 1060 is an extender resin with fluidifying properties specially recommended for applications requiring low viscosity level.

	ISO reference	Value	Units
Viscosity Index	(ISO 1628-2)	105	ml/g
K-value	(ISO 1628-2)	65	
Mean diameter	internal	25 - 35	microns

## Properties:

### Resin

PS 1060 resin can be added to any application and at up to 40 % of the PVC total in some formulations.

### Plastisols


Its addition to a plastisol produced from microsuspension or emulsion PVC allows:

- Reduction of viscosity and viscosity stabilisation during storage,
- Reduction of plastisol dilatancy,
- Improvement of mattness for top coat or wear layer,
- Improvement of transparency and thermal stability whilst ensuring acceptable mechanical properties.

## Example:

Viscosity measurement at high shear levels using a capillary viscometer shows the fluidifying effect of PS 1060 for the formulation below:

PVC PB 1704H	100-x
PVC extender PS 1060	x
DOP	30
BBP	10
DDB	5
Epoxydised Soya Bean Oil	3
Stabiliser Ba/Zn	2



### Packaging and storage:

PS 1060 resin is packed in 25 kg bags, packed and wrapped with stretched film on pallets.

It can also be delivered in bulk.

The resin must be stored in a dry place and at moderate temperature. Under such conditions, the recommended storage can exceed 18 months.

For information on the precautions for the use of PS 1060 resin, please refer to the product's Safety Data Sheet.

### General Information:

Further processing information and recommendations can be obtained from our Technical Service department or our representatives.

Réf.	Edition n°	Date
BU PVC	08.01	04/2008

---

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.