

LUCALOR PEY795Y220

CPVC Compound for Extrusion of Pressure Pipes

Technical Data Sheet

	Values	Units	Standards
SPECIFIC GRAVITY	1.52	g/cm ³	ASTM D 792
HEAT DEFLECTION TEMPERATURE (annealed 24h at 100°C)	234	°F	ASTM D 648
TENSILE STRESS AT YIELD	7 540	psi	ASTM D 638
TENSILE STRESS AT BREAK	7 540	psi	ASTM D 638
TENSILE MODULUS OF ELASTICITY	394 000	psi	ASTM D 638
IZOD IMPACT STRENGTH	3.6	ft-lbf/in	ASTM D 256
OXYGEN INDEX	62	%	ASTM D 2863
FLAMMABILITY UL 94	V-0	-	ASTM D 635
WATER ABSORPTION (24h at 23°C)	1.97 10⁻⁶	lb/in ²	ASTM D 570

Comments

- CPVC Compound for Extrusion (Tan)
- Cell Class **23447-B** (according to ASTM D 1784)
- PEY795Y220 is certified to NSF Standard 14
- PEY795Y220 complies with the requirements of ANSI/NSF Standard 61



The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment on our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

PVC Business Unit
 Quai Louis Aulagne, BP 35
 69191 St Fons Cedex
www.arkema.com

Réf.	Édition n°	Date
BU PVC	3.0	06/2008

info.lacovyl@arkema.com
www.lacovyl.com